




**DESCRIPTION: HIGH TENACITY POLYPROPYLENE FABRIC COATED WITH POLYOLEFINS**  
(1)

**AVAILABLE WIDTHS: Up to 500 cm**

<b>THICKNESS (mm)</b>		<b>042</b>
<b>TOTAL MASS (g/m<sup>2</sup>)</b>		<b>300</b>
<b>FABRIC MASS (g/m<sup>2</sup>)</b>		<b>140</b>
<b>MECHANICAL PROPERTIES</b> (Comparable to PVC coated fabrics)	<b>Breaking Load (daN/50mm)</b>	<b>L: 175 T: 118</b>
	<b>Trapezoidal Tear Strength (daN)</b>	<b>L: 25 T: 16</b>
<b>SERVICE TEMPERATURE RANGE</b>		<b>-15°C to 70°C</b>
<b>WELDABILITY</b>		<b>Hot air</b>
<b>INK COMPATIBILITY</b> (2)		<b>Solvent, Eco-Solvent, Latex</b> (3) <b>and UV Inks</b>

**RECYCLABILITY**

<b>International code</b>		
<b>Information for reprocessing</b>	<b>Extrusion details (Processing temperature range)</b>	<b>165°C to 180°C (T<sub>die</sub> ≈ 175°C)</b>
	<b>Injection Moulding details (Processing temperature range)</b>	<b>165°C to 190°C (T<sub>inj</sub> ≈ 185°C)</b>

Disclaimer: The information supplied in this technical sheet is for guidance only and should not be construed as warranty of any kind. This document is not legal binding and is based on average results from current production. Unless otherwise stated, values cannot be considered as minimum to be satisfied. Purchaser is fully responsible for determining the product suitability for its intended application. Technical details are subject to change without prior notice. Please contact *Media One Digital Imaging Solutions, LLC* for any additional information you may require.