

---

3.75-mil, intermediate calendered PVC film in white with a gloss finish.

Features:

- >Release Paper: 90 gsm PE-coated silicone paper
- >Adhesive: Grey, solvent-based, permanent adhesive

Technical Data

Thickness (without protective paper and adhesive)	3.75 mil
Dimensional Stability (FINAT TM-14)	Adhered to steel, no shrinkage in cross direction; in length, <.016"
Temperature Resistance	Adhered to aluminum, -40°F to +176°F, no variation
Fire Behavior (DIN 75200)	Adhered to steel, self-extinguishing
Fire Rating	ASTM E 84-07 Class "A"
Adhesive Power (FINAT TM-1, after 24 h, average)	Adhered to stainless steel: 4.1 lb/in
Tensile Strength (DIN EN ISO 527)	
Along	Min. 19 MPa
Across	Min. 19 MPa
Elongation at Break (DIN EN ISO 527)	
Along	Min. 130%
Across	Min. 150%
Seawaterability (DIN 50 021)	Adhered to aluminum, after 100h/73°F, no variation
Shelf Life (68°F/50% relative humidity)	2 years
Minimum Application Temperature	46°F
Minimum Life Expectancy (based on accepted application procedures on vertical surfaces)	5 years (Unprinted)

It is recommended that printed film is allowed to dry for at least 24 hours at 70°F (48-72 preferred) before applying a laminate.

Applications:

- >For general signage, and other medium term, flat, indoor and outdoor applications.

Available Sizes:

Finished Rolls	Core	Print Side
54" X 150'	2"	PSO