

3.75-mil, intermediate calendered PVC film in white with a matte finish.

Features:

- >Release Paper: 90 gsm PE-coated silicone paper
- >Adhesive: Grey, solvent-based, permanent adhesive

Technical Data

Thickness (without protective paper and adhesive)	3.75 mil
Dimensional Stability (FINAT TM-14)	Adhered to steel, no shrinkage in cross direction; In length, <.016"
Temperature Resistance	Adhered to aluminum, -40°F to +176°F, no variation
Fire Behavior (DIN 75200)	Adhered to steel, self-extinguishing
Fire Rating	ASTM E 84-07 Class "A"
Adhesive Power (FINAT TM-1, after 24 h, average)	Adhered to stainless steel: 4.1 lb/in
Tensile Strength (DIN EN ISO 527)	
Along	Min. 19 MPa
Across	Min. 19 MPa
Elongation at Break (DIN EN ISO 527)	
Along	Min. 130%
Across	Min. 150%
Seawaterability (DIN 50 021)	Adhered to aluminum, after 100h/73°F, no variation
Shelf Life (68°F/50% relative humidity)	2 years
Minimum Application Temperature	46°F
Minimum Life Expectancy (based on accepted application procedures on vertical surfaces)	5 years (Unprinted)

It is recommended that printed film is allowed to dry for at least 24 hours at 70°F (48-72 preferred) before applying a laminate.

Applications:

- >For general signage, and other medium term flat indoor and outdoor applications.

Available Sizes:

Finished Rolls	Core	Print Side
54" X 150'	2"	PSO
60" X 150'	2"	PSO

Disclaimer: The information supplied in this technical sheet is for guidance only and should not be construed as warranty of any kind. This document is not legal binding and is based on average results from current production. Unless otherwise stated, values cannot be considered as minimum to be satisfied. Purchaser is fully responsible for determining the product suitability for its intended application. Technical details are subject to change without prior notice. Please contact *Media One Digital Imaging Solutions, LLC* for any additional information you may require.