



Coronado™

	Construction	Material	Weight	Thickness	Max Width
TXCO	Woven	100% Coated PES	8.0oz/sq.yd	0.23 mm	126in.
TXCO +W-RY	Woven	100% Recycled PES			
TXCO +W-T	Woven	100% Uncoated PES			

Description

Very high color brilliance

Features

Crease free, No folding, Very soft

Applications

Displays | Banners | Tablecloth

Ink Compatibility

Dye Sub Transfer | Dye Sub Direct

Print Side

Sublimation | Both

Shrink (l):	1.53%
Shrink (w):	0.40%
Stretch (l):	1.87%
Stretch (w):	1.47%
Stretch at Burst (l):	77.00%
Stretch at Burst (w):	70.00%
Burst Strength (l):	281lbs/in.
Burst Strength (w):	162 lbs/in.
Tensile Strength (l):	4 lbs/in.
Tensile Strength (w):	7 lbs/in.
Burst Strength:	192 lbs
Yellowing:	1 dE
Max Roll Length:	100m
Available Recycled:	Yes
Available Anti-microbial:	Yes



NFPA-701 flame Retardant certified.

Recommended transfer settings for sublimation are
374°F-410°F for 40-100 seconds at 40psi.