

CushionTex™

Product Code	Construction	Material	Weight	Thickness	Max Width
TXCT	Woven	100% Coated PES/FR	6.19 oz/sq.yd	0.39 mm	126 in.
TXCT-T	Woven	100% Uncoated PES			320 cm

Description

100% Woven Coated PES for interior, exterior furniture application

Features

Durable woven Coated PES

Applications

Cushion Covers | Beanbags

Ink Compatibility

Dye Sub Transfer | Direct

Print Side

Sublimation | Both

Shrink (l):	1.70%
Shrink (w):	0.50%
Stretch (l):	0.80%
Stretch (w):	1.10%
Stretch at Burst (l):	31.00%
Stretch at Burst (w):	22.00%
Burst Strength (l):	395 lbs/in.
Burst Strength (w):	247 lbs/in.
Tensile Strength (l):	18 lbs/in.
Tensile Strength (w):	14 lbs/in.
Burst Strength:	335 lbs
Yellowing:	1.17 dE
Max Roll Length:	_m
Available Recycled:	Yes
Available Anti-microbial:	Yes



All fabrics are NFPA-701 flame Retardant
Certified/B1 M1 Certifications Available on Request.
Recommended transfer settings for sublimation are
374°F-190°C°F for 40 seconds at 40psi.