





Half-Moon Bay™

Product Code	Construction	Material	Weight	Thickness	Max Width
TXHBL	Warp-knit	100% Polyester	10.12 oz/ sq.yd 343 GSM	0.83 mm	126 in.
 TXHBL-RY					
 TXHBL-AM					

Description  
Heavy Knit Backlit

Features  
Premium, Great Opacity, Excellent Durability

Applications  
Led Lightbox | Popups | Awnings & Tents

Ink Compatibility  
UV | Solvent | Latex

Cutter Compatibility  
Any

Shrink (l):	1.00%	<div><div>LOW</div></div>
Shrink (w):	1.00%	<div><div>LOW</div></div>
Stretch (l):	3.04%	<div><div>LOW</div></div>
Stretch (w):	3.20%	<div><div>LOW</div></div>
Stretch at Burst (l):	104.00%	<div><div>MED</div></div>
Stretch at Burst (w):	59.00%	<div><div>LOW</div></div>
Burst Stregth (l):	74 lbs/in.	<div><div>LOW</div></div>
Burst Strength (w):	464 lbs/in.	<div><div>HIGH</div></div>
Tensile Strength (l):	7 lbs/in.	<div><div>LOW</div></div>
Tensile Strength (w):	16 lbs/in.	<div><div>MED</div></div>
Burst Strength:	334 lbs	<div><div>HIGH</div></div>
Yellowing:	_ dE	<div></div>
Max Roll Length:	100m	
Available Recycled:	Yes	
Available Anti-microbial:	Yes	



NFPA-701 flame retardance certified.  
Recommended transfer settings for sublimation are  
374°F-410°F for 40-100 seconds at 40psi.