



Manhattan™

Product Code	Construction	Material	Weight	Thickness	Max Width
TX3W	Woven	100% Polyester	7.43 oz/sq.yd	0.65 mm	126 in.
 TX3W-RY			252 GSM		
 TX3W-AM					

Description

Woven Triple-White

Features

Premium, Good Opacity, Fantastic Image Quality

Applications

SEG | Tradeshow | Backdrop | Popup | Display | Blockout

Ink Compatibility

Dye Sub Transfer | Dye Sub Direct | UV | Latex

Cutter Compatibility

Hot Knife / Laser Only

Shrink (l):	1.10%	<div><div>MED</div></div>
Shrink (w):	0.73%	<div><div>LOW</div></div>
Stretch (l):	2.67%	<div><div>LOW</div></div>
Stretch (w):	53.00%	<div><div>MED</div></div>
Stretch at Burst (l):	47.00%	<div><div>LOW</div></div>
Stretch at Burst (w):	33.00%	<div><div>LOW</div></div>
Burst Strength (l):	367 lbs/in.	<div><div>HIGH</div></div>
Burst Strength (w):	339 lbs/in.	<div><div>MED</div></div>
Tensile Strength (l):	10 lbs/in.	<div><div>MED</div></div>
Tensile Strength (w):	13 lbs/in.	<div><div>MED</div></div>
Burst Strength:	398 lbs	<div><div>HIGH</div></div>
Yellowing:	0.74 dE	<div><div>LOW</div></div>
Max Roll Length:	100m	
Available Recycled:	Yes	
Available Anti-microbial:	Yes	



NFPA-701 flame retardance certified.
Recommended transfer settings for sublimation are
374°F-410°F for 40-100 seconds at 40psi.