

Monarch™

Product Code	Construction	Material	Weight	Thickness	Max Width
TXMT	Woven	100% Coated PES/FR	6.45 oz/sq.yd	0.48 mm	126in.
TXMT-RY	Woven	100% Recycled PES			
TXMT-T	Woven	100% Uncoated PES			

Description

Curtain

Features

Transparent, Strong, Ideal for Wind, Wind Absorbing

Applications

Flags | Mesh | Fence | Graphics

Ink Compatibility

Dye Sub Transfer | Dye Sub Direct

Print Side

Sublimation | Both

Shrink (l):	1.83%
Shrink (w):	0.67%
Stretch (l):	2.13%
Stretch (w):	2.27%
Stretch at Burst (l):	50.00%
Stretch at Burst (w):	40.00%
Burst Strength (l):	287 lbs/in.
Burst Strength (w):	224 lbs/in.
Tensile Strength (l):	12 lbs/in.
Tensile Strength (w):	11 lbs/in.
Burst Strength:	263 lbs
Yellowing:	0.62 dE
Max Roll Length:	100m
Available Recycled:	Yes
Available Anti-microbial:	Yes



All fabrics are NFPA-701 flame Retardant
Certified/B1 M1 Certifications Available on Request.
Recommended transfer settings for sublimation are
374°F-190°C°F for 40 seconds at 40psi.