





Media Data Sheet Newport™

Newport™

Product Code	Construction	Material	Weight	Thickness	Max Width
TXJWB	Warp-knit	100% Polyester	9.32 oz/sq.yd	0.49 mm	126 in.
 TXJWB-RY			316 GSM		
 TXJWB-AM					

Description

White-Backed Blockout Fabric

Features

White Resin Coating

Applications

Display | Pop-Up | Backdrops | SEG

Ink Compatibility

Dye Sub Transfer | Dye Sub Direct | UV | Latex

Cutter Compatibility

Any

Shrink (l):	1.27%	MED
Shrink (w):	0.37%	LOW
Stretch (l):	1.47%	LOW
Stretch (w):	1.33%	LOW
Stretch at Burst (l):	74.00%	LOW
Stretch at Burst (w):	98.00%	MED
Burst Strength (l):	94 lbs/in.	LOW
Burst Strength (w):	162 lbs/in.	LOW
Tensile Strength (l):	4 lbs/in.	LOW
Tensile Strength (w):	7 lbs/in.	LOW
Burst Strength:	192 lbs	MED
Yellowing:	1 dE	LOW
Max Roll Length:	100m	
Available Recycled:	Yes	
Available Anti-microbial:	Yes	



NFPA-701 flame retardance certified.
Recommended transfer settings for sublimation are
374°F-410°F for 40-100 seconds at 40psi.