





Media Data Sheet Table Rock™

Table Rock™

Product Code	Construction	Material	Weight	Thickness	Max Width
TXTC	Woven	100% Polyester	5.08 oz/sq.yd	0.48 mm	126 in.
 TXTC-RY			172 GSM		
 TXTC-AM					

Description

Tablecloth

Features

Durable, Soft, Wrinkle Free, Ideal for Draping

Applications

Tablecloths | Restaurants | Catering | Food Service


Ink Compatibility

Dye Sub Transfer | Dye Sub Direct

Cutter Compatibility

Hot Knife / Laser Only

Shrink (l):	1.83%	HIGH
Shrink (w):	0.67%	LOW
Stretch (l):	2.13%	LOW
Stretch (w):	2.27%	LOW
Stretch at Burst (l):	50.00%	LOW
Stretch at Burst (w):	40.00%	LOW
Burst Strength (l):	287 lbs/in.	MED
Burst Strength (w):	224 lbs/in.	MED
Tensile Strength (l):	12 lbs/in.	MED
Tensile Strength (w):	11 lbs/in.	MED
Burst Strength:	263 lbs	MED
Yellowing:	0.62 dE	LOW
Max Roll Length:	m	
Available Recycled:	Yes	
Available Anti-microbial:	Yes	



NFPA-701 flame retardance certified.

Recommended transfer settings for sublimation are
374°F-410°F for 40-100 seconds at 40psi.