

Venice™

| Product Code | Construction | Material | Weight | Thickness | Max Width |
|--------------|--------------|--------------------|---------------|-----------|-----------|
| Textent | Woven 600D | 100% Coated PES/FR | 9.77 oz/sq.yd | 0.40 mm | 126 in. |
| Textent-RY | Woven 600D | 100% Recycled PES | | | |
| Textent-T | Woven 600D | 100% Uncoated PES | | | |

Description

Strong Fabric For Short-Term Outdoor Use

Features

Water Resistant Acrylic Coating, Strong Tensile Tear Strength

Applications

Tent | Tradeshow | Outdoor Ad | Awnings & Promotions

Ink Compatibility

Dye Sub Transfer | Dye Sub Direct | UV | Latex

Print Side

Sublimation | Outside

Shrink (l):

—

Shrink (w):

—

Stretch (l):

0.40%

Stretch (w):

0.40%

Stretch at Burst (l):

32.00%

Stretch at Burst (w):

17.00%

Burst Strength (l):

468 lbs/in.

Burst Strength (w):

230 lbs/in.

Tensile Strength (l):

18 lbs/in.

Tensile Strength (w):

15 lbs/in.

Burst Strength:

308 lbs

Yellowing:

2.22 dE

Max Roll Length:

150m

Available Recycled:

Yes

*Made with 100% Recycled Plastic Bottles

Available Anti-microbial:

Yes



All fabrics are NFPA-701 flame Retardant
Certified/B1 M1 Certifications Available on
Request.

Recommended transfer settings for sublimation are
374°F-190°C°F for 40 seconds at 40psi.